

Alloy 410S stainless steel is a low carbon modification of Type 410 stainless steel. Low carbon and optionally a small addition of titanium and/ or columbium minimize austenite formation at high temperatures, thereby restricting the alloy's ability to harden. The material remains soft and ductile even when the material is rapidly cooled from above the critical temperature. This low hardening characteristic helps to prevent cracking when the steel is welded or exposed to high temperatures. The alloy is completely ferritic in the annealed condition. 410S is ferromagnetic.

## **Specifications** UNS: S41008 W. Nr./EN: 1.4000 ASTM: A 240 ASTM: SA-240 Chemical Composition, % Cr Ni Si Р Mn S Fe C MIN 11.5 \_ \_ \_ \_ \_ \_ \_ 13.5 1.0 0.08 MAX 0.6 1.0 0.04 0.03 balance **Features** Increased weldability over 410 • Maintains ductility even when heated and quenched **Applications** • Tower packing • Distillation trays • Automotive exhaust components • Quenching racks **Physical Properties** Density: 0.280 lb/in<sup>3</sup> Melting Range: 2700 - 2790°F Temperature, °F 212 600 1000 1200 Coefficient of Thermal Expansion\* 6.4 6.7 7.5 6.0 in/in°F x 10<sup>-6</sup> 187 **Thermal Conductivity** \_ \_ \_ Btu ● ft/ft<sup>2</sup> ● hr ● °I Modulus of Elasticity, Dynamic 29.0 \_ \_ \_ psi x 106 \* 70°F to indicated temperature. **Mechanical Properties Tensile Properties** Minimum (Plate) Typical Ultimate Tensile Strength, ksi 60 64.4 0.2% Yield Strength, ksi 30 42 22 33 Elongation, % 89 (max) 75 Hardness, Rb

180

pass

Cold Bend, °



## The Global Leader in Specialty Metals



Bulletin No. 121USe 07/12 warranty and assumes no legal liability or responsibility for results to be obtained in any particular situation, and shall not be liable for any direct, indirect, special, or consequential damage therefrom. This material is subject to revision without prior notice.